

Resurfacing powder coatings

Instructions for painting over powder coatings with a two-component liquid paint

Preparation

The substrate must be generally dry and free of grease, oils, release agents and drawing compounds, dirt, corrosion products and other contaminants. The Brillux powder coating must be sanded for this purpose.

The surface must be cleaned with mild solvents (such as mineral spirits, isopropanol or ethanol) to remove sanding and other residues. Use a lint-free, soft cloth for this purpose.

Resurfacing

Prime coat The prepared dry surface can be primed with Brillux 2C Epoxy Primer 5706. A 2-Component PUR paint can be applied directly instead.

The primer can be painted over with a weatherproof paint after a period of at least 6 hours. We recommend using Brillux 2C PUR Acrylic Paint 5740/5741/5742 or 5743.

Sanding If the waiting period between applying the primer and the topcoat is more than 48 hours, sand and clean the primer surface before applying the topcoat. Do this the same way as the preparation procedure.

Remarks

This Technical Information is based on intense development work and many years of practical experience. The contents do not constitute any contractual relationship. The user/buyer is not released from his/her obligation to test our products for suitability for the intended application. In addition, our General Terms and Conditions shall apply.

As soon as a new edition of this Technical Information is issued, the previous specifications become invalid. If you need the current version, please contact your Brillux consultant. Version 2

Brillux GmbH & Co. KG Industrielack
Otto-Hahn-Straße 14
59423 Unna
Tel. +49 2303 8805-0
Fax +49 2303 8805-119
info@brillux-industrielack.de
www.brillux-industrielack.de